VICTOR® PLASTIC CEMENT





PRODUCT DESCRIPTION

Basic Use

CEMEX Victor® plastic cement is specially formulated and manufactured to produce masonry mortar for use in brick, block and stone construction as well as cementitious veneer.

Composition and Materials

CEMEX plastic cement consists of a mixture of portland cement, limestone, and chemical admixtures to provide plasticizing properties and other enhanced performance attributes. These components are proportioned at the cement plant under controlled conditions to assure product consistency.

Types

CEMEX plastic cement conforms to ASTM C1328 and ASTM C91 for Type S and Type M masonry cements.

Limitations

Plastic cement is not approved for use in loadbearing structural masonry construction in seismic zones 2, 3 and 4.

INSTALLATION

Follow the application instructions included in Appendix X1 of ASTM C926.

TECHNICAL DATA

Applicable Standards

The following standards apply to the use of CEMEX plastic cement:

ASTM C91 Standard Specifications for Masonry Cements

ASTM C144 Standard Specification for Aggregates for Masonry Mortar

ASTM C270 Standard Specification for Mortar for Unit Masonry

ASTM C780 Standard Test Method for Preconstruction and Construction Evaluation of Mortar for Plain and Reinforced Unit Masonry

ASTM C926 Standard Specification for Application of Portland Cement-Based Plaster

ASTM C1328 Standard Specification for Plastic (Stucco) Cement

Property Specifications

CEMEX plastic cement conforms to the property specifications of ASTM C1328.

Packaging

CEMEX plastic cement is available in bulk or 94 lb. bags.

Availability

CEMEX plastic cement can be ordered by contacting the CEMEX Sales at 1-800-99-CEMEX (23639)

WARRANTY

CEMEX warrants that the products identified are in accordance with the appropriate current ASTM specifications. No one is authorized to make any modifications or addition to this warranty. CEMEX makes no warranty or representation, either expressed or implied with respect to this product and disclaims any implied warranty of merchantability or fitness for a particular purpose.

As CEMEX has no control over other ingredients mixed with this product or the final application, CEMEX does not and cannot warrant the finished work.

In no event shall CEMEX be liable for direct, indirect, special, incidental or consequential damages arising out of the use of this product, even if advised of the possibility of such damages. In no case shall CEMEX's liability exceed the purchase price of this product.

TECHNICAL SERVICES

CEMEX personnel are available to provide technical assistance by contacting 1-800-99-CEMEX (1-800-992-3639).

U.S. OPERATIONS HEADQUARTERS 929 Gessner Rd, Suite 1900 HOUSTON, TEXAS 77024 (713) 650-6200, (800) 999-8529 www.cemexusa.com